

In-vitro Antibacterial Activity of Lactobacilli Metabolites Loaded Hydrogel Formulations against *Pseudomonas aeruginosa*

Antibacterial Activity of Metabolites Loaded Formulations

Suna Sibel Gurpinar¹, Burcu Devrim², Mujde Eryilmaz^{1*}

¹ Department of Pharmaceutical Microbiology, Faculty of Pharmacy, Ankara University
Ankara, Turkey

² Department of Pharmaceutical Technology, Faculty of Pharmacy, Ankara University
Ankara, Turkey

*Corresponding Author:

Mujde Eryilmaz,

Ankara University, Faculty of Pharmacy, Department of Pharmaceutical Microbiology,
Ankara, TURKEY

e-mail: meryilmaz@ankara.edu.tr

Phone number: 0 507 292 00 76

ABSTRACT

Pseudomonas aeruginosa is an opportunistic pathogen that may cause serious infections, ranging from localized skin infections to life-threatening systemic diseases. It is one of the resistant bacteria which leads to failure in the treatment. New treatment strategies are urgently needed for the treatment of infections caused by resistant bacteria. Researchers are interested in *Lactobacillus* species because of their antimicrobial effective metabolites. The aim of this study was comparing the antibacterial activity of lactobacilli metabolites loaded chitosan and Pluronic F127 hydrogel formulations. Metabolites loaded hydrogel formulations were prepared by adding 20 µl of supernatant into the polymer solutions. The antimicrobial activities of two hydrogel formulations were investigated against *P. aeruginosa* using Agar Spot Method. Metabolites loaded chitosan hydrogel formulations were found to be effective against *P. aeruginosa*. No antibacterial activity was observed for metabolites loaded Pluronic

F127 hydrogel formulations. When we compare these two hydrogel formulations, we observed that hydrogel formulation prepared by using chitosan released effective metabolites but Pluronic F127 hydrogel formulation couldn't release antibacterial effective metabolites. The antibacterial effect of metabolites loaded chitosan hydrogel formulation suggests that this formulation could be used as an alternative treatment option in *P. aeruginosa* skin infections. However, further investigations are needed to develop a pharmaceutical product.

Keywords: *Lactobacillus sp.*, bacterial metabolites, antimicrobial activity, chitosan, Pluronic F127

INTRODUCTION

Antibiotic resistance is a serious public health problem that threatens the whole world. Day by day, new multi-resistant microorganisms have increasingly been reported from different regions of the world. Failure in the treatment of these resistant bacteria leads scientists to investigate alternative treatment options¹⁻³.

Lactobacillus genus, which is grouped among lactic acid bacteria, comprises of Gram-positive, facultative anaerobic or microaerophilic, non-spore-forming, rod-shaped bacteria. These bacteria produce lactic acid as the major metabolic end-product of carbohydrate fermentation. Some groups of them also produce various amounts of compounds such as acetic acid, carbon dioxide, and ethyl alcohol^{4,5}. *Lactobacilli* are the normal flora members of the human body and they commonly found in the mouth, vagina, and intestines⁶. Owing to their metabolites and antagonistic effects, they protect the human body from pathogens⁷. In a healthy premenopausal woman, the dominance of *lactobacilli* in the vagina is protective against the colonization of pathogenic microorganisms⁸. In recent years, the number of studies reporting the beneficial effects of flora microorganisms on human health has increased. The genus *Lactobacillus* has taken considerable attention because of their antimicrobial, immunomodulatory, anti-inflammatory and anti-carcinogenic activities. These microorganisms have been the subject of many investigations to find out whether they can be used as an alternative for the treatment of diseases^{3, 9-12}.

Chitosan, a deacetylated derivative of chitin, is a cationic polymer that consists of a long chain formed by a combination of β -1,4-D-glucosamine (deacetylated unit) and N-acetyl-D-glucosamine (acetylated unit) by linking with β (1-4) glycosidic bonds. As a natural polymer, it demonstrates incredible properties such as biocompatibility, biodegradability, non-toxicity, antimicrobial activity, and adsorption capability. Therefore, it has been extensively studied for its use in many fields. Chitosan is also widely used as a wound dressing due to its excellent hemostatic properties and antimicrobial activities. Its antimicrobial activity has been explained by several theories. The most accepted hypothesis is that its action on bacteria would occur by the loss of its intercellular components. Due to its positive charge, it binds to the bacterial membrane causing a change in permeability and the output of its intercellular components, thus leading to cell death. The antimicrobial activity of chitosan was observed against a wide variety of microorganisms, including fungi, algae, and bacteria, being more active against Gram-positive bacteria than Gram-negative ones¹³⁻¹⁵.

Poloxamers, poly(ethylene oxide)–poly(propylene oxide)–poly(ethylene oxide) triblock copolymers (PEO–PPO–PEO), are synthetic polymers with thermoreversible behavior in aqueous solutions and widely used in pharmaceutical systems. They are available in different molecular weights with commercial name pluronics. Among pluronics, F127 is widely explored for drug delivery due to its thermo-reversible gelation properties, ability to solubilize hydrophobic solutes and to form micellar structure (incorporate both hydrophilic and hydrophobic drugs) and extending drug release and non-toxicity. Moreover, Pluronic F127 gels have also exhibited improvement in wound healing by stimulating expression of vascular epithelial growth factor and (VEGF) and transforming growth factor (TGF- β 1)¹⁶⁻¹⁷.

The aim of this study was comparing the antibacterial activity of vaginal lactobacilli metabolites loaded chitosan and Pluronic F127 hydrogel formulations against *Pseudomonas aeruginosa*.

MATERIALS AND METHODS

***Lactobacillus* sp. Isolates**

In this study, metabolites of the seven *L. gasseri*, two *L. crispatus*, and one *L. helveticus* vaginal isolates which were previously identified in terms of species-level by analyzing the 16S rRNA gene sequence and found effective against some test bacteria were used³.

Obtaining metabolites

Lactobacillus isolates grown on Rogosa Agar for 24-48 hours were inoculated into tubes containing De Man-Rogosa Sharpe Broth (Merck, Germany), at 37 °C, under anaerobic conditions for 72 hours. After the incubation period, cells were removed by centrifugation (12000 g, 10 min, 4 °C). The cell-free supernatants were filter-sterilized (0.45 μ m pore size) (Minisart, Germany)^{3,18}.

Preparation of Chitosan and Pluronic Hydrogels

Chitosan was dissolved in 1% acetic acid solution at room temperature with continuous mechanical stirring to obtain a 1% (w/w) solution¹³. Metabolite loaded chitosan hydrogel was made by adding 20 μ l of supernatant into the chitosan solution.

Pluronic F127 hydrogel (20 wt%) was prepared by gradually adding under magnetic stirring at 4 °C Pluronic F127 powder to distilled water. The temperature was maintained at 4 °C until complete dissolution of Pluronic F127 powder¹⁹. Metabolite containing Pluronic F127 hydrogel was prepared by gradually adding 20 μ l of supernatant into the Pluronic F127 solution under magnetic stirring at 4 °C.

Antimicrobial Activity Test

The antimicrobial activities of the metabolite loaded hydrogel formulations were investigated against *Pseudomonas aeruginosa* ATCC 27853 using Agar Spot Method²⁰. Test bacteria culture grown for 18-24 hours, adjusted to McFarland 0.5, were inoculated onto Mueller-Hinton Agar plate with sterile swabs. 20 μ L of each of metabolite loaded hydrogel formulations and supernatant were dropped equidistantly onto media inoculated with test bacteria. *Lactobacilli* supernatants as positive control were used. All the plates were incubated at 37 °C for 18-24 hours, under aerobic conditions. After incubation, the growth inhibition in Agar Spot Method was considered as a positive effect.

RESULTS and DISCUSSION

Five *L. gasseri*, one *L. crispatus*, and *L. helveticus* metabolites loaded chitosan hydrogel formulations were found to be effective against *P. aeruginosa*. Although chitosan alone had antibacterial activity, it was found that the metabolites loaded chitosan formulations showed better antibacterial activity.

Besides that, Pluronic F127 hydrogel formulation didn't provide antimicrobial activity as metabolites couldn't release from hydrogel formulation. This is thought to be due to the high viscosity of the Pluronic F127 hydrogel with a concentration of 20%. When we compare these two hydrogel formulations, we observed that hydrogel formulation prepared by using chitosan released effective metabolites and therefore antimicrobial activity could be observed.

CONCLUSION

In conclusion, the antibacterial effect of vaginal *Lactobacillus* metabolites loaded chitosan hydrogel formulation suggests that effective metabolite loaded this formulation could be used in the treatment of *P. aeruginosa* skin infections. However, further investigations are needed to develop a pharmaceutical product.

ACKNOWLEDGMENTS

This study is a continuation of a previously published study. We thank Prof. Dr. Devran Gerceker and Dr. Haluk Guriz for their contributions.

CONFLICT OF INTEREST

The author(s) confirm that they have no conflict of interest.

AUTHOR'S CONTRIBUTION

All authors contributed to the study design, data collection, data analysis, data interpretation, and manuscript preparation.

REFERENCES

1. World Health Organization. Implementation of the global action plan on antimicrobial resistance. www.who.int/antimicrobial-resistance/news/WHO-GAP-AMR-Newsletter-may-2017.pdf?ua=1 (Accessed May 17, 2019).
2. Islam, M.A.; Islam, M.; Hasan, R.; Hossain, M.I.; Nabi, A.; Rahman, M.; Goessens, W.H.F.; Endtz, H.P.; Boehm, A.B.; Faruque, S.M. Environmental spread of NDM-1-producing multi-drug resistant bacteria in Dhaka, Bangladesh. *Appl Environ Microbiol*, 2017; 83.
3. Eryılmaz M, Gürpınar SS, Palabıyık İM, Güriz H, Gerçeker D. Molecular identification and antimicrobial activity of vaginal *Lactobacillus* sp. *Current Pharmaceutical Biotechnology*, 2018; 19(15):1241-1247.

4. Huang CH, Li SW, Huang L, Watanabe K. Identification and classification for the *Lactobacillus casei* group. *Front Microbiol.* 2018; 9:1974.
5. Kandler O, Weiss N. Regular. Nonsporing Gram-Positive Rods. In: Murray RGE, Brenner DJ, Bryant MP, Holt JG, Krieg NR, Moulder JW, Pfennig N, Sneath PHA, Staley JT. *Bergey's Manual of Systematic Bacteriology*. 2nd ed. USA: Williams and Wilkins; 1986:1208-1234.
6. Davoodabadi A, Dallal MMS, Lashani E, Ebrahimi MT. Antimicrobial activity of *Lactobacillus* spp. isolated from fecal flora of healthy breast-fed infants against diarrheagenic *Escherichia coli*. *Jundishapur J Microb.* 2015; 8:1-6.
7. Kılıç E, Aslım B. Laktik asit bakterilerinin vajen florasındaki önemi ve probiyotik olarak kullanımı. *OrLab On-line Mikrobiyoloji Dergisi.* 2003; 1:70-82.
8. Kovachev S. Defence factors of vaginal lactobacilli. *Crit Rev Microbiol.* 2017; 8:1-9.
9. Bashiardes S, Tuganbaev T, Federici S, Elinav E. The microbiome in anti-cancer therapy. *Semin Immunol.* 2017; 32:74-81.
10. Gopalakrishnan V, Helmink BA, Spencer CN, Reuben A, Wargo JA. The Influence of the Gut Microbiome on Cancer, Immunity, and Cancer Immunotherapy. *Cancer Cell.* 2018; 33:570-580.
11. Sgibnev AV, Kremleva EA. Vaginal protection by H₂O₂-producing Lactobacilli. *Jundishapur J Microb.* 2015;8.
12. Dimitonova SP, Danova ST, Serkedjieva JP, Bakalov BV. Antimicrobial activity and protective properties of vaginal lactobacilli from healthy Bulgarian women. *Anaerobe* 2007; 13:178-84.
13. Ouyang QQ, Hu Z, Lin ZP, Quan WY, Deng YF, Li SD, Li PW, Chen Y. Chitosan hydrogel in combination with marine peptides from tilapia for burns healing. *International Journal of Biological Macromolecules.* 2018; 112:1191-1198.
14. Frade ML, de Annunzio SR, Calixto GMF, Victorelli FD, Chorilli M, Fontana CR. Assessment of Chitosan-Based Hydrogel and Photodynamic Inactivation against *Propionibacterium acnes*. *Molecules.* 2018; 23(2):E473.
15. Figueroa-Pizano MD, Vélaz I, Peñas FJ, Zavala-Rivera P, Rosas-Durazo AJ, Maldonado-Arce AD, Martínez-Barbosa ME. Effect of freeze-thawing conditions for preparation of chitosan-poly (vinyl alcohol) hydrogels and drug release studies. *Carbohydr Polym.* 2018; 195:476-485.
16. Baloglu E, Karavana SY, Senyigit ZA, Guneri T. Rheological and mechanical properties of poloxamer mixtures as a mucoadhesive gel base. *Pharm Dev Technol.* 2011; 16(6):627-636.
17. Alavi T, Rezvanian M, Ahmad N, Mohamad N, Ng SF. Pluronic-F127 composite film loaded with erythromycin for wound application: formulation, physicomechanical and in vitro evaluations. *Drug Deliv Transl Res.* 2017; doi: 10.1007/s13346-017-0450-z.
18. Stoyancheva G, Marzotto M, Dellaglio F, Torriani S. Bacteriocin production and gene sequencing analysis from vaginal *Lactobacillus* strains. *Arch Microbiol.* 2014; 196:645-653.
19. Malli S, Bories C, Pradines B, Loiseau PM, Ponchel G, Bouchemal K. In situ forming pluronic® F127/chitosan hydrogel limits metronidazole transmucosal absorption. *European Journal of Pharmaceutics and Biopharmaceutics,* 2017; 112:143-147.
20. Benli M, Yiğit N. Ülkemizde yaygın kullanımı olan kekik (*Thymus vulgaris*) bitkisinin antimikrobiyal aktivitesi. *Orlab On-Line Mikrobiyoloji Dergisi.* 2005; 3:1-8.